

Amstep Model DSA4, 4 inches wide. Tread 3/8 inches thick, lip 1/4 from underside, with continuous anchor 3/4 inches deep. Length 6 inches less than overall length of poured step. Homogenous epoxy abrasive formulation formed and cured on an extruded aluminum base, alloy 6063-T6.

Coefficient of friction 0.99 dry, 0.93 wet per ASTM F 609. Abrasive filler color as selected.